


ALCANTARA® 0.8

Alcantara® 0.8 Cod. 5033

APPLICATIONS Accessories - Apparel

MAIN CHARACTERISTICS

COMPOSITION	ALCANTARA®	POLYESTER POLYURETHANE	67 ± 3 % 33 ± 3 %
THICKNESS			0.83 ± 0.10 mm
UNIT WEIGHT		UNI EN 29073-1	220 ± 30 g/m ²
WIDTH			≥ 142 cm
DIMENSIONAL STABILITY (WATER 40°C)		UNI EN ISO 25077 + 6330	≤ 3 %
BREAKING LOAD	LENGTHWISE CROSSWISE	UNI EN 29073-3	≥ 155 N/5cm ≥ 115 N/5cm
TEAR STRENGTH	LENGTHWISE CROSSWISE	EN ISO 13937-2	≥ 10 N ≥ 10 N
ELONGATION AT 50N	LENGTHWISE CROSSWISE	UNI EN 29073-3	≥ 2 % ≥ 10 %
MARTINDALE ABRASION 12 kPa		EN ISO 12947-4	(*) 2000 cycles
COLOR FASTNESS			
TO LIGHT	Xenotest Beta 36h	UNI EN ISO 105 B02	≥ 5.5 blue scale (1-8)
TO DOMESTIC WASHING	Tone change Staining	EN ISO 105 C06	≥ 4 grey scale (1-5) ≥ 3 grey scale (1-5)
TO DRY CLEANING	Tone change Staining	AATCC 132	≥ 4 grey scale (1-5) ≥ 3 grey scale (1-5)
TO RUBBING	Dry Wet	EN ISO 105 X12	≥ 4 grey scale (1-5) ≥ 3 grey scale (1-5)
TO PERSPIRATION	Acid - Basic	EN ISO 105 E04	≥ 4.5 grey scale (1-5)
GENERAL WASHING			

(*) Slight change in the appearance of product surface.

ORDINE MINIMO / Minimum order quantities (MOQ)

5 mt per colore dove sottolineato _____ / 5 mt per color if underlined _____

NOTE: Tra i bagni di tintura, sono possibili leggere variazioni di tono dovute al processo di lavorazione.

Nel caso di inserti o manufatti realizzati con più materiali, verificare sempre la compatibilità dei diversi materiali.

NOTE: Slight shade variations from one production batch to another one are possible on these products.

In case of items manufactured using different materials, always verify the compatibility of the same.

