


ALCANTARA® 1.1

Alcantara® 1.1 Cod.5183

APPLICATIONS Accessories - Apparel

MAIN CHARACTERISTICS			
COMPOSITION	ALCANTARA®	POLYESTER POLYURETHANE	71 ± 3 % 29 ± 3 %
THICKNESS			1.10 ± 0.15 mm
UNIT WEIGHT		EN 29073-1	350 ± 40 g/m2
WIDTH			≥ 142 cm
DIMENSIONAL STABILITY	Water 40°C	EN 25077 + EN ISO 6330	≤ 3 %
BREAKING LOAD	LENGTHWISE CROSSWISE	EN ISO 13934-1	≥ 400 N ≥ 400 N
ELONGATION AT 50N	LENGTHWISE CROSSWISE	EN ISO 13934-1	≥ 2 % ≥ 6 %
TEAR STRENGTH		EN ISO 13937-3	≥ 30 N
MARTINDALE ABRASION 12 kPa	END POINT	EN ISO 12947-4 EN ISO 12947-2	(*) ≥ 20000 cycles ≥ 100000 cycles
COHESION Alcantara Backing		EN ISO 2411	≥ 10 N
SLIPPAGE RESISTANCE OF YARNS AT SEAM	LENGTHWISE CROSSWISE	EN ISO 13936-2	≤ 6 mm
RESISTANCE TO PILLING	2000 cycles	EN ISO 12945-2	≥ 4/5
COLOR FASTNESS			
TO LIGHT	Xenotest Beta	EN ISO 105 B02	≥ 5 blue scale (1-8)
TO DOMESTIC WASHING	Tone change Staining	EN ISO 105 C06	≥ 4 grey scale (1-5) ≥ 3 grey scale (1-5)
TO DRY CLEANING	Tone change Staining	AATCC 132	≥ 4 grey scale (1-5) ≥ 3 grey scale (1-5)
TO RUBBING	Dry Wet	EN ISO 105 X12	≥ 4 grey scale (1-5) ≥ 3 grey scale (1-5)
TO WATER	Tone change Staining	EN ISO 105 E01	≥ 4 grey scale (1-5) ≥ 3.5 grey scale (1-5)
GENERAL WASHING			

(*) Slight change in the appearance of product surface.

ORDINE MINIMO / Minimum order quantities (MOQ)

5 mt per colore dove sottolineato / 5 mt per color if underlined

NOTE: Tra i bagni di tintura, sono possibili leggere variazioni di tono dovute al processo di lavorazione.

Nel caso di inserti o manufatti realizzati con più materiali, verificare sempre la compatibilità dei diversi materiali.

NOTE: Slight shade variations from one production batch to another one are possible on these products.

In case of items manufactured using different materials, always verify the compatibility of the same.

