

EST. 1972

PASHMA



P210 MOCHA
0.8 1.1

P200 FLAX
0.8 1.1

P010 CONCRETE
0.8 1.1

P000 FLEECE
0.8 1.1

P110 AVIO
0.8 1.1

P100 DENIM
0.8 1.1



ALCANTARA® 0.8

Alcantara® 0.8		Cod. 5033	
APPLICATIONS	Accessories - Apparel		
MAIN CHARACTERISTICS			
COMPOSITION	ALCANTARA®	POLYESTER POLYURETHANE	67 ± 3 % 33 ± 3 %
THICKNESS			0.83 ± 0.10 mm
UNIT WEIGHT		UNI EN 29073-1	220 ± 30 g/m2
WIDTH			≥ 142 cm
DIMENSIONAL STABILITY (WATER 40°C)		UNI EN ISO 25077 + 6330	≤ 3 %
BREAKING LOAD	LENGTHWISE CROSSWISE	UNI EN 29073-3	≥ 155 N/5cm ≥ 115 N/5cm
TEAR STRENGTH	LENGTHWISE CROSSWISE	EN ISO 13937-2	≥ 10 N ≥ 10 N
ELONGATION AT 50N	LENGTHWISE CROSSWISE	UNI EN 29073-3	≥ 2 % ≥ 10 %
MARTINDALE ABRASION 12 kPa		EN ISO 12947-4	(*) 2000 cycles
COLOR FASTNESS			
TO LIGHT	Xenotest Beta 36h	UNI EN ISO 105 B02	≥ 5.5 blue scale (1-8)
TO DOMESTIC WASHING	Tone change Staining	EN ISO 105 C06	≥ 4 grey scale (1-5) ≥ 3 grey scale (1-5)
TO DRY CLEANING	Tone change Staining	AATCC 132	≥ 4 grey scale (1-5) ≥ 3 grey scale (1-5)
TO RUBBING	Dry Wet	EN ISO 105 X12	≥ 4 grey scale (1-5) ≥ 3 grey scale (1-5)
TO PERSPIRATION	Acid - Basic	EN ISO 105 E04	≥ 4.5 grey scale (1-5)
GENERAL WASHING			

(*) Slight change in the appearance of product surface.

ORDINE MINIMO / Minimum order quantities (MOQ)

5 mt per colore dove sottolineato — / 5 mt per color if underlined —

NOTE: Tra i bagni di tintura, sono possibili leggere variazioni di tono dovute al processo di lavorazione.

Nel caso di inserti o manufatti realizzati con più materiali, verificare sempre la compatibilità dei diversi materiali.

NOTE: Slight shade variations from one production batch to another one are possible on these products.

In case of items manufactured using different materials, always verify the compatibility of the same.



ALCANTARA® 1.1

Alcantara® 1.1		Cod. 5183	
APPLICATIONS		Accessories - Apparel	
MAIN CHARACTERISTICS			
COMPOSITION	ALCANTARA®	POLYESTER POLYURETHANE	71 ± 3 % 29 ± 3 %
THICKNESS			1.10 ± 0.15 mm
UNIT WEIGHT		EN 29073-1	350 ± 40 g/m2
WIDTH			≥ 142 cm
DIMENSIONAL STABILITY	Water 40°C	EN 25077 + EN ISO 6330	≤ 3 %
BREAKING LOAD	LENGTHWISE CROSSWISE	EN ISO 13934-1	≥ 400 N ≥ 400 N
ELONGATION AT 50N	LENGTHWISE CROSSWISE	EN ISO 13934-1	≥ 2 % ≥ 6 %
TEAR STRENGTH		EN ISO 13937-3	≥ 30 N
MARTINDALE ABRASION 12 kPa	END POINT	EN ISO 12947-4 EN ISO 12947-2	(*) ≥ 20000 cycles ≥ 100000 cycles
COHESION Alcantara Backing		EN ISO 2411	≥ 10 N
SLIPPAGE RESISTANCE OF YARNS AT SEAM	LENGTHWISE CROSSWISE	EN ISO 13936-2	≤ 6 mm
RESISTANCE TO PILLING	2000 cycles	EN ISO 12945-2	≥ 4/5
COLOR FASTNESS			
TO LIGHT	Xenotest Beta	EN ISO 105 B02	≥ 5 blue scale (1-8)
TO DOMESTIC WASHING	Tone change Staining	EN ISO 105 C06	≥ 4 grey scale (1-5) ≥ 3 grey scale (1-5)
TO DRY CLEANING	Tone change Staining	AATCC 132	≥ 4 grey scale (1-5) ≥ 3 grey scale (1-5)
TO RUBBING	Dry Wet	EN ISO 105 X12	≥ 4 grey scale (1-5) ≥ 3 grey scale (1-5)
TO WATER	Tone change Staining	EN ISO 105 E01	≥ 4 grey scale (1-5) ≥ 3.5 grey scale (1-5)
GENERAL WASHING			

(*) Slight change in the appearance of product surface.

ORDINE MINIMO / Minimum order quantities (MOQ)

5 mt per colore dove sottolineato / 5 mt per color if underlined

NOTE: Tra i bagni di tintura, sono possibili leggere variazioni di tono dovute al processo di lavorazione.

Nel caso di inserti o manufatti realizzati con più materiali, verificare sempre la compatibilità dei diversi materiali.

NOTE: Slight shade variations from one production batch to another one are possible on these products.

In case of items manufactured using different materials, always verify the compatibility of the same.

